

Design: JS_1LAF3
Reference Wavelength: 510.00
Incident Angle: 0.0

Layer	Material	Refractive Index	Extinction Coefficient	Optical Thickness
Medium	Air	1.0000	0.0000000	
1	SOL-GEL_50%	1.2311	0.0000000	0.23853270
2	MgF2	1.3845	0.0000000	0.25100260
3	LaF3	1.5760	0.0000000	0.13858810
4	SOL-GEL_50%	1.2311	0.0000000	0.01897833
5	LaF3	1.5760	0.0000000	0.01852836
Substrate	OHARA_PBM18Y_Glass	1.6035	0.0000000	