

Design: JS_6LAF3
Reference Wavelength: 510.00
Incident Angle: 0.0

Layer	Material	Refractive Index	Extinction Coefficient	Optical Thickness
Medium	Air	1.0000	0.0000000	
1	SOL-GEL_50%	1.2311	0.0000000	0.25996400
2	MgF2	1.3845	0.0000000	0.03529171
3	LaF3	1.5760	0.0000000	0.07031707
4	SOL-GEL_50%	1.2311	0.0000000	0.07180385
5	LaF3	1.5760	0.0000000	0.18011020
6	MgF2	1.3845	0.0000000	0.02608162
7	LaF3	1.5760	0.0000000	0.35347070
8	SOL-GEL_50%	1.2311	0.0000000	0.02755526
9	LaF3	1.5760	0.0000000	0.18349210
10	SOL-GEL_50%	1.2311	0.0000000	0.05489784
11	LaF3	1.5760	0.0000000	0.16717740
12	SOL-GEL_50%	1.2311	0.0000000	0.03996693
13	MgF2	1.3845	0.0000000	0.01405857
14	SOL-GEL_50%	1.2311	0.0000000	0.00618116
15	LaF3	1.5760	0.0000000	0.19091870
16	SOL-GEL_50%	1.2311	0.0000000	0.02431840
Substrate	OHARA_PBM18Y_Glass	1.6035	0.0000000	